

Restricted equivalence of paired epsilon-negative and mu-negative layers to a negative phase-velocity material (*alias* left-handed material)

Akhlesh Lakhtakia¹

CATMAS — Computational and Theoretical Materials Science Group

Department of Engineering Science and Mechanics

Pennsylvania State University, University Park, PA 16802-6812, USA

Clifford M. Krowne

Microwave Technology Branch

Electronic Science & Technology Division

Naval Research Laboratory, Washington, DC 20375-5347, USA

Abstract: The time-harmonic electromagnetic responses of (a) a bilayer made of an epsilon-negative layer and a mu-negative layer, and (b) a single layer of a negative phase-velocity material are compared. Provided all layers are electrically thin, a restricted equivalence between (a) and (b) exists. The restricted equivalence depends on the linear polarization state and the transverse wavenumber. Implications for perfect lenses and parallel-plate waveguides are considered.

Key words: Negative real permittivity, Negative real permeability, Negative phase velocity, Parallel-plate waveguide, Perfect lens, Phase velocity, Poynting vector

¹Corresponding author. Tel: +1 814 863 4319; Fax: +1 814 865 9974; E-mail: AXL4@PSU.EDU

1 Introduction

This communication is inspired by the ongoing spate of papers published on the inappropriately designated *left-handed materials* which are macroscopically homogeneous and display negative phase velocities in relation to the time-averaged Poynting vector, but are not chiral [1]. Nominally, such a material is deemed to possess a relative permittivity scalar $\epsilon_r = \epsilon'_r + i\epsilon''_r$ and a relative permeability scalar $\mu_r = \mu'_r + i\mu''_r$, both dependent on the angular frequency ω , such that both $\epsilon'_r < 0$ and $\mu'_r < 0$ in some spectral regime.² Originally conceived by Veselago [2], these materials have been artificially realized quite recently [3,4]. Their fascinating electromagnetic properties can have technological implications of massive proportions [5], but those implications remain speculative at this time. Although these materials have been variously named LHM, we prefer the name *negative phase-velocity* (NPV) materials as the least ambiguous of all extant names.

Using transmission-line analysis and lumped parameters, Alu and Engheta [6] have recently suggested a new route to realizing NPV materials: Take a thin layer of an *epsilon-negative* (EN) material: it has a negative real permittivity scalar but a positive real permeability scalar. Stick it to a thin layer of a *mu-negative* (MN) material, which has a negative real permeability scalar and a positive real permittivity scalar. Provided the two layers are sufficiently thin, the paired EN–MN layers *could* function effectively as a NPV material. The clear attraction of this scheme is that EN and MN layers are easier to manufacture, very likely, than the NPV materials fabricated thus far [3,4].

Our objective here is to examine the suggested scheme using continuum field theory, and to establish a restricted equivalence of an EN–MN bilayer to a NPV material. Implications

²The condition for the phase velocity and the time-averaged Poynting vector to be oppositely directed is $(|\epsilon_r| - \epsilon'_r)(|\mu_r| - \mu'_r) > \epsilon''_r\mu''_r$, which permits — more generally — ϵ'_r and/or μ'_r to be negative LHM. An $\exp(-i\omega t)$ time-dependence having been assumed here, $\epsilon''_r > 0$ and $\mu''_r > 0$ at all $\omega > 0$ for all passive materials.

for parallel-plate waveguides Engh and perfect lenses P2 are deduced therefrom.

A note about notation: Vectors are in boldface, column vectors are boldface and enclosed in square brackets, while matrixes are denoted by Gothic letters; ϵ_0 and μ_0 are the free-space permittivity and permeability, respectively; and $k_0 = \omega(\epsilon_0\mu_0)^{1/2}$ is the free-space wavenumber. A cartesian coordinate system is used, with $\mathbf{u}_x$, $\mathbf{u}_y$ and $\mathbf{u}_z$ as the unit vectors.

2 Bilayer Theory in Brief

Consider the layers $0 < z < d_a$ and $d_a < z < d_a + d_b$. Their constitutive relations are as follows:

$$\left. \begin{aligned} \mathbf{D}(\mathbf{r}) &= \epsilon_0 \epsilon_a \mathbf{E}(\mathbf{r}) \\ \mathbf{B}(\mathbf{r}) &= \mu_0 \mu_a \mathbf{H}(\mathbf{r}) \end{aligned} \right\}, \quad 0 < z < d_a, \quad (1)$$

$$\left. \begin{aligned} \mathbf{D}(\mathbf{r}) &= \epsilon_0 \epsilon_b \mathbf{E}(\mathbf{r}) \\ \mathbf{B}(\mathbf{r}) &= \mu_0 \mu_b \mathbf{H}(\mathbf{r}) \end{aligned} \right\}, \quad d_a < z < d_a + d_b. \quad (2)$$

The constitutive parameters present in the foregoing equations are complex-valued with positive imaginary parts (as befits any passive medium). The two half-spaces on either sides of the bilayer are vacuum.

Without loss of generality, the electromagnetic field phasors everywhere can be written as K1

$$\left. \begin{aligned} \mathbf{E}(\mathbf{r}) &= \tilde{\mathbf{e}}(z) e^{i\kappa x} \\ \mathbf{H}(\mathbf{r}) &= \tilde{\mathbf{h}}(z) e^{i\kappa x} \end{aligned} \right\}, \quad -\infty < z < \infty, \quad (3)$$

where the transverse wavenumber $\kappa \in [0, \infty)$. The fields inside the bilayer must follow the 4×4 matrix ordinary differential equation K1,L1

$$\frac{d}{dz} [\mathbf{f}(z)] = i\mathcal{P}(z) [\mathbf{f}(z)], \quad 0 < z < d_a + d_b. \quad (4)$$

In this equation, $[\mathbf{f}(z)] = \text{col} [\tilde{e}_x(z), \tilde{e}_y(z), \tilde{h}_x(z), \tilde{h}_y(z)]$ is a column vector, while the 4×4 matrix function $\mathcal{P}(z)$ is piecewise uniform as

$$\mathcal{P}(z) = \begin{cases} \mathcal{P}_a, & 0 < z < d_a \\ \mathcal{P}_b, & d_a < z < d_a + d_b \end{cases}, \quad (5)$$

where

$$\mathcal{P}_{a,b} = \begin{bmatrix} 0 & 0 & 0 & -\frac{\kappa^2}{\omega\epsilon_0\epsilon_{a,b}} + \omega\mu_0\mu_{a,b} \\ 0 & 0 & -\omega\mu_0\mu_{a,b} & 0 \\ 0 & -\omega\epsilon_0\epsilon_{a,b} + \frac{\kappa^2}{\omega\mu_0\mu_{a,b}} & 0 & 0 \\ \omega\epsilon_0\epsilon_{a,b} & 0 & 0 & 0 \end{bmatrix}. \quad (6)$$

The only nonzero elements of the matrixes $\mathcal{P}_{a,b}$ appear on their antidiagonals, of which the (2,3) and the (3,2) elements are relevant to s -polarized fields, and the (1,4) and the (4,1) elements to the p -polarized fields.

The solution of $\mathring{\text{diff}}_{\text{eq}}$ is straightforward, because the matrix $\mathcal{P}(z)$ is piecewise uniform. Thus, the algebraic relation

$$[\mathbf{f}(d_b + d_a)] = e^{i\mathcal{P}_b d_b} e^{i\mathcal{P}_a d_a} [\mathbf{f}(0)] \quad (7)$$

is sufficient to solve both reflection/transmission problems as well as guided-wave propagation problems. The two matrix exponentials on the right side of $\mathring{\text{sys}}$ cannot be interchanged — unless the matrixes $\mathcal{P}_a$ and $\mathcal{P}_b$ also commute, which is possible with dissimilar materials *only* in quite special circumstances L1,L2.

3 Analysis

Matrixes $\mathcal{P}_{a,b}$ have $\pm\sqrt{k_0^2\epsilon_{a,b}\mu_{a,b} - \kappa^2} = \pm\alpha_{a,b}$ as their eigenvalues. Provided that $|\alpha_{a,b}| d_{a,b} \ll 1$ (i.e., both layers are electrically thin), the approximations

$$e^{i\mathcal{P}_{a,b}d_{a,b}} \simeq \mathcal{I} + i\mathcal{P}_{a,b}d_{a,b} \quad (8)$$

can be made, with $\mathcal{I}$ as the 4×4 identity matrix. Then

$$e^{i\mathcal{P}_b d_b} e^{i\mathcal{P}_a d_a} \simeq \mathcal{I} + i\mathcal{P}_a d_a + i\mathcal{P}_b d_b \simeq e^{i\mathcal{P}_a d_a} e^{i\mathcal{P}_b d_b}, \quad (9)$$

and the two layers in the bilayer can be interchanged without significant effect Reese.

Let us now consider a single layer of relative permittivity ϵ_{eq} , relative permeability μ_{eq} and thickness d_{eq} . Quantities $\mathcal{P}_{eq}$ and α_{eq} can be defined in analogy to $\mathcal{P}_a$ and α_a . Two thickness ratios are defined as

$$p_{a,b} = \frac{d_{a,b}}{d_{eq}} \geq 0, \quad (10)$$

in order to compare the single layer with the previously described bilayer. There is no hidden restriction on the non-negative real numbers p_a and p_b .

Provided that $|\alpha_{eq}| d_{eq} \ll 1$ (i.e., the single layer is electrically thin as well), the approximation

$$e^{i\mathcal{P}_{eq} d_{eq}} \simeq \mathcal{I} + i\mathcal{P}_{eq} d_{eq} \quad (11)$$

can be made. Equations 10 and 11 permit us to establish the following equivalences between a bilayer and a single layer:

- (i) *s-polarization*: The only nonzero field components are E_y , H_x and H_z . Therefore, the equality of the (2,3) elements of $p_a \mathcal{P}_a + p_b \mathcal{P}_b$ and $\mathcal{P}_{eq}$, and likewise of the (3,2) elements, has to be guaranteed for equivalence; thus, the equations

$$p_a \mu_a + p_b \mu_b = \mu_{eq}, \quad (12)$$

$$p_a \epsilon_a + p_b \epsilon_b - \left(\frac{\kappa}{k_0} \right)^2 \left(\frac{p_a}{\mu_a} + \frac{p_b}{\mu_b} \right) = \epsilon_{eq} - \left(\frac{\kappa}{k_0} \right)^2 \frac{1}{\mu_{eq}} \quad (13)$$

have to be solved for ϵ_{eq} and μ_{eq} . We conclude therefrom that, for a given value of κ and subject to the thickness restrictions $|\alpha_{a,b,eq}| d_{a,b,eq} \lesssim 0.1$, the bilayer and a single layer are equivalent with respect to the transformation of the x - and y - components of the fields from one exterior face to the other exterior face if

$$\epsilon_{eq} = p_a \epsilon_a + p_b \epsilon_b$$

$$- \left(\frac{\kappa}{k_0} \right)^2 \left[\frac{p_a p_b (\mu_a - \mu_b)^2}{\mu_a \mu_b (p_a \mu_a + p_b \mu_b)} + \frac{(p_a + p_b + 1)(p_a + p_b - 1)}{p_a \mu_a + p_b \mu_b} \right], \quad (14)$$

$$\mu_{eq} = p_a \mu_a + p_b \mu_b. \quad (15)$$

(ii) *p-polarization*: The only nonzero field components being H_y , E_x and E_z , the equality of the (1, 4) elements of $p_a \mathcal{P}_a + p_b \mathcal{P}_b$ and $\mathcal{P}_{eq}$ suffices, along with the equality of the (4, 1) elements of the two matrixes. For a given value of κ and subject to the thickness restrictions $|\alpha_{a,b,eq}| d_{a,b,eq} \lesssim 0.1$, the bilayer and a single layer are equivalent if

$$\begin{aligned} \mu_{eq} &= p_a \mu_a + p_b \mu_b \\ &\quad - \left(\frac{\kappa}{k_0} \right)^2 \left[\frac{p_a p_b (\epsilon_a - \epsilon_b)^2}{\epsilon_a \epsilon_b (p_a \epsilon_a + p_b \epsilon_b)} + \frac{(p_a + p_b + 1)(p_a + p_b - 1)}{p_a \epsilon_a + p_b \epsilon_b} \right], \end{aligned} \quad (16)$$

$$\epsilon_{eq} = p_a \epsilon_a + p_b \epsilon_b. \quad (17)$$

Clearly, the constitutive parameters of the equivalent layer are functions of both p_a and p_b ; and we must point out that the sum of these two ratios need not equal unity. Furthermore, except for normal incidence (i.e., $\kappa = 0$), the constitutive parameters of the equivalent layer depend on the incident linear polarization state. Finally, the constitutive parameters of the equivalent layer change with the transverse wavenumber κ .

The foregoing equations can be manipulated to yield negative values of both ϵ'_{eq} and μ'_{eq} for either

- an EN–MN bilayer $\{\epsilon'_a < 0, \epsilon'_b > 0, \mu'_a > 0, \mu'_b < 0\}$ or
- a MN–EN bilayer $\{\epsilon'_a > 0, \epsilon'_b < 0, \mu'_a < 0, \mu'_b > 0\}$.

An EN–MN bilayer is equivalent to a NPV layer for both polarization states when $\kappa = 0$, provided the condition

$$\frac{|\mu'_b|}{\mu'_a} > \frac{p_a}{p_b} > \frac{\epsilon'_b}{|\epsilon'_a|} \quad (18)$$

holds true. The inequality δ_1 is applicable for a MN–EN bilayer also, if the subscripts

a and b are interchanged therein, i.e.,

$$\frac{|\mu'_a|}{\mu'_b} > \frac{p_b}{p_a} > \frac{\epsilon'_a}{|\epsilon'_b|}. \quad (19)$$

A further specialization of $p_a + p_b = 1$ leads to the inequality

$$\frac{|\mu'_b|}{\mu'_a + |\mu'_b|} > p_a > \frac{\epsilon'_b}{|\epsilon'_a| + \epsilon'_b} \quad (20)$$

for EN–MN bilayers, and

$$\frac{|\mu'_a|}{\mu'_b + |\mu'_a|} > p_b > \frac{\epsilon'_a}{|\epsilon'_b| + \epsilon'_a} \quad (21)$$

for MN–EN bilayers.

The inequalities δ_1 – δ_4 should be adequate for both s – and p –polarization states when $\kappa/k_0 \ll 1$. In general, however, a given EN–MN (or MN–EN) bilayer is equivalent to a different NPV material for a different linear polarization state and/or transverse wavenumber. Thus, the equivalence between an EN–MN (or a MN–EN) bilayer and a NPV layer is *restricted*.

The restricted equivalence has an interesting implication for perfect lenses P2. A perfect lens of thickness $d > 0$ is defined by the fulfillment of the condition $[\mathbf{f}(d)] = [\mathbf{f}(0)]$ for all ω and κ . Because of dispersion and dissipation, at best, this condition is fulfilled approximately. Let us imagine that the condition is fulfilled by some NPV constitutive parameters for some ω and all $|\kappa| \leq \hat{\kappa}$. Then, the implementation of the acceptably imperfect lens as a cascade of thin EN–MN (or MN–EN) bilayers would require that the successive bilayers have different constitutive parameters and that the entry as well as the exit faces be curved, and even those steps may not suffice. In contrast, κ is fixed for any single–mode parallel–plate waveguide, and so is the range of operating frequencies; and the emulation of a NPV material *via* EN–MN (or MN–EN) bilayers may not be onerous.

References

- [1] Lakhtakia A, McCall MW, Weiglhofer WS: Brief overview of recent developments on negative phase-velocity mediums (alias left-handed materials). Arch. Elektr. Über. **56** (2002) 407–410
- [2] McCall MW, Lakhtakia A, Weiglhofer WS: The negative index of refraction demystified. Eur. J. Phys. **23** (2002) 353–359
- [3] Veselago VS: The electrodynamics of substances with simultaneously negative values of ϵ and μ . Sov. Phys. Usp. **10** (1968) 509–514
- [4] Shelby RA, Smith DR, Schultz S: Experimental verification of a negative index of refraction. Science **292** (2001) 77–79
- [5] Parazzoli CG, Greigor RB, Li K, Koltenbah BEC, Tanielian M: Experimental verification and simulation of negative index of refraction using Snell’s law. Phys. Rev. Lett. **90** (2003) 107401
- [6] Pendry P: Electromagnetic materials enter the negative age. Physics World **14** (9) (2001) 47–51, September issue
- [7] Alu A, Engheta N: Mono-modal waveguides filled with parallel epsilon-negative and mu-negative paired metamaterial layers. 2003 IEEE MTT-S Int. Microw. Symp., Philadelphia, PA, USA, June 8–13, 2003
- [8] Pendry J: Negative refraction makes a perfect lens. Phys. Rev. Lett. **85** (2001) 3966–3969
- [9] Krowne CM: Fourier transformed matrix method of finding propagation characteristics of complex anisotropic layered media. IEEE Trans. Microw. Theory Tech. **32** (1984) 1617–1625

- [10] Lakhtakia A: On perfect lenses and nihility. *Int. J. Infrared Millim. Waves* **23** (2002) 339–343
- [11] Lakhtakia A, Sherwin JA: Orthorhombic materials and perfect lenses. *Int. J. Infrared Millim. Waves* **24** (2003) 19–23
- [12] Hochstadt H: *Differential Equations — A Modern Approach*, Dover Press, New York, NY, USA 1975
- [13] Reese PS, Lakhtakia A: Low-frequency electromagnetic properties of an alternating stack of thin uniaxial dielectric laminae and uniaxial magnetic laminae. *Zeit. Naturforsch. A* **46** (1991) 384–388